# (12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

#### (19) World Intellectual Property Organization International Bureau



# 

### (43) International Publication Date 24 July 2003 (24.07.2003)

## **PCT**

## (10) International Publication Number WO 03/060952 A1

(51) International Patent Classification7: 61/82

H01J 61/36,

(21) International Application Number:

PCT/IB02/05683

(22) International Filing Date:

20 December 2002 (20.12.2002)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data: 02075147.5

15 January 2002 (15.01.2002)

(71) Applicant (for all designated States except US): KONIN-KLIJKE PHILIPS ELECTRONICS N.V. [NL/NL]; Groenewoudseweg 1, NL-5621 BA Eindhoven (NL).

(72) Inventors; and


(75) Intentors/Applicants (for US only): APETZ, Rolf, T., A. [DE/NL]; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL) MULDERIJ, Ton, R. [NL/NL]; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL). BECKERS, Lucas, J., A., M. [NL/NL]; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL).

(74) Agent: DUSSELDORP, Jan, C.; Internationaal Octrooibureau B.V., Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE,

[Continued on next page]

(54) Title: HIGH-PRESSURE DISCHARGE LAMP



The invention relates to a (57) Abstract: high-pressure discharge lamp having a discharge vessel (10) with a ceramic wall (1) which is closed at one end by a plug. The plug (2) is provided with an electrode (3) arranged in the discharge vessel (10). The ceramic wall (1) and the plug (2) are jointed by a fusion joint (4). The fusion joint (4) comprises an alloy comprising substantially molybdenum and aluminum. Preferably, the fusion joint (4) comprises a material selected from the group formed by Al<sub>8</sub>Mo<sub>3</sub>, Al<sub>63</sub>Mo<sub>37</sub>, AL<sub>63</sub>Mo<sub>37</sub>, AlMo, AlMo<sub>3</sub> and combinations of said materials. Preferably, the plug (2) comprises a material selected from the group formed by molybdenum, tungsten and combinations of said materials. Preferably, the ceramic wall (1) comprises aluminum nitride. According to the invention, the plug (2) has a high corrosion resistance.

